

Properties

B45M0C

Flame-retardant PBT/ABS resin

Standard

Properties	Test methods	Test conditions	Units	
Mold shrinkage	Daicel method	-	%	0.6-0.8
Tensile strength	ISO 527	-	MPa	44
Flexural strength	ISO 178	-	MPa	70
Flexural modulus	ISO 178	-	MPa	2500
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m2	7
Deflection temperature under load	ISO 75	1.80MPa	deg C	85
Deflection temperature under load	ASTM D648	1.82MPa/6.4mm	deg C	100
Deflection temperature under load	ISO 75	0.45MPa	deg C	115
Deflection temperature under load	ASTM D648	0.46MPa/6.4mm	deg C	115
Coefficient of linear thermal expansion	ISO 11359	MD	X1E-5/deg C	10
Coefficient of linear thermal expansion	ISO 11359	TD	X1E-5/deg C	-
Flammability	UL94	-	-	V-0/1.2mm
Hot wire ignition	UL746A	1.2mm	sec(PLC)	12(4)
High ampere arc ignition	UL746A	1.2mm	(PLC)	(0)
Water absorption	ISO 62	-	%	0.15
Density	ISO 1183	-	g/cm3	1.32

Note

- Test methods such as ISO standards are fully or almost compliant with the standards.
- Values are typical, not quality assured.
- UL recognition File No. is E47773.
- The colorant formulations are restricted for each UL certified color. Please contact us for more information.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
3-5hrs 80-120deg C	230-250	240-250	220-240	190-230	50-90	5-20	60-80