

Properties

S6500R

Flame-retardant PC/ABS resin

*The product(s) do not contain halogenated compounds as flame retardants and do not contain antimony compounds.

Standard

Properties	Test methods	Test conditions	Units	
Melt mass-flow rate	ISO 1133	220 deg C/10kg	g/10min	45
Melt mass-flow rate	ISO 1133	240 deg C/5kg	g/10min	26
Mold shrinkage	Daicel method	-	%	0.4-0.6
Tensile strength	ISO 527	-	MPa	54
Flexural strength	ISO 178	-	MPa	85
Flexural modulus	ISO 178	-	MPa	2600
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m2	15
Notched Izod impact strength	ASTM D256	23 deg C/6.4mm	J/m	200
Deflection temperature under load	ISO 75	1.80MPa	deg C	79
Deflection temperature under load	ASTM D648	1.82MPa/12.7mm	deg C	85
Flammability	UL94	-	-	V-0/1.6mm 5VA/2.5mm
Water absorption	ISO 62	-	%	0.3
Density	ISO 1183	-	g/cm3	1.16

Note

- Test methods such as ISO standards are fully or almost compliant with the standards.
- Values are typical, not quality assured.
- UL recognition File No. is E47773.
- The colorant formulations are restricted for each UL certified color. Please contact us for more information.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
3-4hrs 80-90deg C	220-250	230-250	210-230	190-210	40-60	5-15	40-60